

PRODUCT DESCRIPTION

LSD™ is a water-based lithium silicate solution used to densify and dustproof concrete and masonry elements. It bonds chemically with the concrete to strengthen and harden floors that are porous, readily absorptive, and only moderately hard.

AFZIR LSD™ product penetrates into the concrete, sealing the pores and capillaries and creating a chemical reaction within the concrete to produce a hard mineral film that is resistant to water, chemicals and abrasion.

PRODUCT FEATURES

- Water-based lithium silicate solution.
- Ready to use product.
- Increases the strength of the surface by filling the pores decreasing porosity while increasing density.
- Quick-drying for fast turnaround
- Less maintenance and up-keep.
- Creates a breathable surface for passage of moisture vapor.
- Does not leave a film and will not make surfaces slippery.
- Short downtime; floors can be put back into service immediately after application.
- Compatible with floor and carpeting adhesives and most stripping paints.
- Seals, densifies and dustproofs in one operation

PRODUCT USES

LSD™ can be used on:

- Interior or exterior horizontal concrete
- Floors and walls requiring a harder
- Office and multi-residential buildings
- Warehouse floors
- Food storage areas
- Diamond polishing concrete
- Docks and ramps

HOW TO USE

SURFACE PREPARATION

- The surface must be clean and free of dirt, oil, curing compounds or foreign materials.
- Patch all cracks and remove any laitance.
- grout and fill cracks as necessary to restore the surface finish
- Rinse, then remove surface water.
- Complete finishing operations and allow visible surface water to dissipate prior to application of LSD™.
- Surface must be able to bear foot traffic without marring or damaging the concrete.

MIXING:

LSD™ is a ready to use product, stir slightly.

APPLICATION:

- LSD™ may be applied by sprayer, roller or brush. To increase the effectiveness of the product, use a mechanical scrubber.
- Continue working until the product begins to gel or become slippery, then re-wet the surface and work for another 10-15 minutes.
- As the surface gels or becomes slippery again, flush with water and squeegee the surface dry.



Lithium Silicate Densifier for Concrete - LSD™

Finally, wait 30 minutes, then flush the surface once more with fresh water and squeegee dry.

- LSD™ should soak into the concrete.
- Additional coats may be applied if the concrete surface is absorptive.

APPLICATION NOTE: In order for the proper reaction to occur, the surface must remain saturated for a minimum of 30 minutes. Very porous or open concrete surfaces may result in faster drying.

TECHNICAL DATA

Consistency	liquid
Colour	Clear
VOC Content	0 g/L
Density	1.1 g/cm ³
PH	12.3
Dry solids content	16 %
Shelf life	2 years
Drying time at 21°C	4 – 24 Hours

Cleaning

Clean brushes, tools, equipment and flush sprayer with potable water immediately after use.

HANDLING

Approved personal protection equipment should be worn at all times. Particle mask is recommended for possible airborne particles. Gloves are recommended when handling mortar to avoid skin irritation. Safety glasses are recommended to prevent eye irritation. Wear chemical resistant clothing/gloves/goggles. Ventilate area. In absence of adequate ventilation, use properly fitted respirator.

STORAGE

Store in unopened containers in a cool, dry area under normal warehouse conditions between 5°C and 40°C. It should be protect from freezing.

FIRST AID

In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with plenty of water; contact physician immediately. For respiratory problems, remove to fresh air. Wash clothing before reuse.

DISCLAIMER OF LIABILITY

AFZIR, LLC warrants its products to be free from manufacturing defects. Buyer determines suitability of

LSD™

Lithium Silicate Densifier for Concrete

product for use and assumes all risks. Buyer's sole remedy shall be limited to replacement of product. Any claim for breach of this warranty must be brought within six months of the date of purchase.

AFZIR shall not be liable for any consequential or special damages of any kind, resulting from any claim or breach of warranty, breach of contract, negligence or any legal theory.

The Buyer, by accepting the products described herein, agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production.